

COLORS COLORES

AQUASTAIN

Ciranova® Aquastain is a water-based color stain based on micro pigments for staining all types of wood for indoor use. Aquastain gives the wood a uniform look and brings out the wood grain.

- » Provides a uniform coloring that accentuates the grain of the wood.
- » Can be finished afterwards with oil or waterborne finish.
- » Colors can be mixed with one another.

AQUASTAIN

Aquastain de Ciranova® es un tinte con base de agua basado en micropigmentos para la coloración de todo tipo de madera para uso interior. Aquastain da a la madera un aspecto uniforme y realza el grano de la madera.

- » Proporciona una coloración uniforme que realza el grano de la madera.
- » Puede ser acabado posteriormente con aceite o barniz al agua.
- » Todos los colores pueden mezclarse con otros.

TECHNICAL DATA

Product type:	waterborne
Cleaning:	water
Number of colors:	16 colors
Coverage:	220-320 sq.ft./L / 830 - 1200 sq.ft./gal
Drying times:	2-3 hours
Sanding grit:	P 100-120
Storage/transport:	between 5°C and 25°C
Disposal:	Dispose of residue and empty packaging in accordance with local ordinances.

DATOS TÉCNICOS

Tipo de producto:	base de agua
Limieza:	agua
Número de colores:	16 colores
Rendimiento:	220-320 sq.ft./L / 830 - 1200 sq.ft./gal
Tiempo de secado:	2-3 horas
Grano de lijado:	P 100-120
Almacenamiento/transporte:	entre 5 °C y 25 °C
Desecho:	Deseche los residuos y envases vacíos de acuerdo con sus ordenanzas locales.



1L



PREPARATION

Make sure that all old finish coats are completely removed and that the wood is free from dust and other dirt. Can be used on sanded, planed, and brushed wood. Pre-wetting the wood can reduce the risk of overlapping.

APPLICATION

Stir and shake well before and during use.

Aquastain must be evenly applied with a roller or brush in the direction of the woodgrain. After +/- 2 minutes, remove the excess with a lint-free cloth.

FINISHING

After the Aquastain has dried, it must be protected with a product of the Ciranova® range such as Hardwaxoil Magic, UN1CO, Fortico. For more information, you can consult the relevant technical data sheets. When using a waterborne finish it is recommended to intermediately sand before applying the last protective layer.

IMPORTANT INFORMATION ⚠

Only use corrosion-resistant materials. Clean all materials with water immediately afterwards. The final color depends on the wood type, sanding, preparation and the amount applied. **That is why it is recommended to always test the color beforehand!**