

WATERBORNE FINISHES

PRODUCTOS DE ACABADO CON BASE DE AGUA

EASY FLOW MATT-SATIN

1 component water-based PU acrylate for parquet and wooden surfaces. Gives a clear protection to the wood. Easy to use, universal and neutral in overlaps

- » Good application properties
- » Easy to apply
- » Good chemical and mechanical resistance

EASY FLOW MATE-SATINADO

1 componente de acrilato de poliuretano a base de agua para parquet y superficies de madera. Dota a la madera de una protección transparente. Fácil de usar, universal y neutro en los solapamientos.

- » Buenas propiedades de aplicación.
- » Fácil de aplicar.
- » Buena resistencia química y mecánica.

TECHNICAL DATA

Product type:	waterborne
Cleaning:	water
Viscosity:	+/-25 sec - DIN 4mm
Solid content:	+/- 31%
Gloss level:	Matt 15 / Satin 40
Coverage:	100-130 sq.ft./L per coat
Drying times:	Dust dry: after 20 to 30 minutes Sandable: after 4 to 6 hours Load-bearing: after 24 hours Fully cured: after +/- 7 days
Sanding grit:	P 120-150
Storage/transport:	between 5°C and 25°C
Disposal:	Dispose of residue and empty packaging in accordance with local ordinances

DATOS TÉCNICOS

Tipo de producto:	base de agua
Limieza:	Agua
Viscosidad:	+/-25 sec - DIN 4mm
Materias sólidas:	+/- 31%
Grado de brillo:	Mate 15 / Satinado 40
Rendimiento:	100-130 sq.ft./L por capa
Tiempos de secado:	Antiadherente al polvo: después de 20 a 30 minutos Se puede lijar: después de 4 a 6 horas Soporta peso ligero: después de 24 horas Totalmente endurecido: después de +/- 7 días
Grano de lijado:	P 120-150
Almacenamiento/transporte:	entre 5°C y 25°C
Desecho:	Deseche los residuos y envases vacíos de acuerdo con sus ordenanzas locales.



5L



PREPARATION

Make sure all prior coatings are completely removed and the wood surface is free from dust and other contamination. Can be used on sanded, planed and brushed wood. For under-floor heating, exotic wood and cork,

APPLICATION

Use EASY FLOW 1C as a primer and finishing coat. Apply the product by brush or roller in 3 coats. First coat: apply approx. 80-100 g/m² and leave to dry for approx. 4 hours. Second coat: apply approx. 80-100 g/m² in the same manner as the first coat and leave to dry for +/- 6 hours. Before applying the 3th coat intermediate sanding with 180-220 grain, remove dust and apply the third coat approx. 80-100 g/m².

* 1m² = 10,76 sq.ft.

Drying times are dependent on the applied quantity, temperature, humidity and ventilation.

MAINTENANCE

Regular maintenance with Hard Floor Fresh Ciranova®. Use UNICARE X-MATT or Hard floor Polish for periodic maintenance. Hard Floor Cleaner Ciranova® is used for cleaning highly soiled floors and to remove old layers of polish.

IMPORTANT INFORMATION ⚠

Only use corrosion-resistant materials. Clean all materials with water immediately after use. For industrial applications, the Ciranova® technical service should be consulted. **Once the package is opened, skin formation is possible after contact with air, filter before use.**