

WATERBORNE FINISHES

PRODUCTOS DE ACABADO CON BASE DE AGUA

FORTICO 2C NF / NATURAL-MATT-SATIN

2 component, PU waterborne finish for parquet floors subject to heavy traffic. Fortico 2C is extremely scratch-resistant and does not burnish. Fortico 2C can be easily applied without overlapping or roller imprints. FORTICO 2C has been specifically developed for heavy traffic parquet floors, such as commercial spaces, hotels, restaurants, etc.

- » Extremely scratch resistant thanks to anti-scratch technology.
- » High wear resistance.
- » Doesn't burnish.
- » Provides an invisible finish.

FORTICO 2C NF / NATURAL-MATE-SATINADO

Lacado para parqués de PU de 2 componentes con base de agua, para parqués y suelos de madera que soportan grandes cargas. FORTICO 2C es extremadamente resistente a rozaduras y no produce reflejos. FORTICO 2C puede aplicarse fácilmente sin solapamiento ni marcas de rodillo. FORTICO 2C se ha desarrollado específicamente para suelos de parqué muy transitados, como espacios comerciales, hoteles, restaurantes, etc.

- » Extremadamente resistente a rozaduras gracias a su tecnología antiarañazos.
- » Alta resistencia al desgaste.
- » No produce reflejos.
- » Da un acabado invisible.

TECHNICAL DATA

Product type:	waterborne
Viscosity:	+/-20 sec - DIN 4mm
Solid content:	+/- 32%
Gloss level:	Matte 15-25 - Satin 45-50 - Natural >10
Mixing ratio:	100/10
Potlife:	+/- 3 hours after adding the hardener
Cleaning:	Water
Coverage:	100-125 sq.ft./L per coat 380 - 470 sq.ft./gal per coat
Drying times:	Dust dry: after 2 hours Sandable: after 3 to 5 hours Lightly walkable: after 24 hours Fully cured: After +/- 7 days
Sanding grit:	P 120-150
Storage/transport:	between 5°C and 25°C
Disposal:	Dispose of residue and empty packaging in accordance with local ordinances.

DATOS TÉCNICOS

Tipo de producto:	base de agua
Viscosidad:	+/- 20 s - DIN 4 mm
Materias sólidas:	+/- 32 %
Grado de brillo:	Mate 15-25 - Satinado 45-50 - Natural >10
Proporción de mezcla:	100/10
Potlife:	+/- 3 horas tras añadir el endurecedor
Limieza:	agua
Rendimiento:	100-125 sq.ft./L por capa 380 - 470 sq.ft./gal por capa
Tiempo de secado:	Seco al polvo: tras 2 horas Lijable: tras 3 a 5 horas Pueden colocarse cargas encima: tras 24 horas Completamente endurecido: Tras +/- 7 días
Grano de lijado:	P 120-150
Almacenamiento/transporte:	entre 5 °C y 25 °C
Desecho:	Deseche los residuos y envases vacíos de acuerdo con sus ordenanzas locales.



5L
+
500 ml



PREPARATION

Make sure that all old finish coats are completely removed and that the wood is free from dust and other dirt. Can be used on sanded, planed, and brushed wood. For a lighter and more natural finish, WOODLOOK PLUS can be used as a primer first.

APPLICATION

FORTICO 2C can be used as primer and finishing coat. Mix the waterborne finish with the hardener at 10 to 1 (10%). Let the product settle for 15 minutes. Apply the product in 3 layers with a brush or roller. First layer: apply ca. 7.50 - 9.50 g/sq.ft and let dry for +/- 4 hours. Second layer: apply ca. 7.50 - 9.50 g/sq.ft in the same manner as the first layer and let dry for +/- 6 hours. Afterwards intermediate sanding with grain 180-220, make it dust-free and apply the third layer at ca. 7.50 - 9.50 g/sq.ft.

FINISHING

FORTICO can be used as a primer and finishing coat.

MAINTENANCE

Regular maintenance with Ciranova® Hard Floor Fresh. For periodic maintenance, use UNICARE X-MATT for natural & matt finish and Hard Floor Polish for the satin finish. Ciranova® Hard Floor Cleaner is used for cleaning highly soiled floors and to remove old layers of polish.

IMPORTANT INFORMATION ⚠

Only use corrosion-resistant materials. Clean all materials with water immediately afterwards. For industrial applications, the Ciranova® technical service should be consulted. **Water-based products can develop skins after contact with air. Filter beforehand, if necessary.**