

OILS ACEITES

HARDWAXOIL MAGIC

Modified parquet oil with excellent wear resistance. Good filling, natural color, and excellent chemical and mechanical resistance. Gives a very matte finish. The resistance can be further improved by adding a UA hardener.

- » Matte, natural finish that maintains the natural appearance of the wooden surface.
- » Fast-drying.
- » Excellent chemical resistance.

HARDWAXOIL MAGIC

Aceite de parquet modificado con una resistencia excelente al desgaste. Buenas propiedades de rellenado, color natural y excelente resistencia química y mecánica. Acabado muy mate que no produce reflejos con el tiempo. La resistencia puede mejorarse añadiendo un endurecedor de UA.

- » Acabado mate y natural que mantiene el aspecto natural de superficies de madera.
- » Secado rápido.
- » Resistencia excelente a productos químicos.

TECHNICAL DATA

Product type:	Solvent-based
Viscosity:	+/- 50 sec - DIN 4mm
Solid content:	+/- 47%
Gloss level:	Ultra matte
Mixing ratio:	Optional hardener UA: 100/5
Potlife:	+/- 3 hours after adding the hardener
Cleaning:	Cleaning Thinner Ciranova®
Number of colors:	16 colors
Coverage:	450-550 sq.ft./L per coat 1700 - 2080 sq.ft./gal per coat
Drying times:	Recoatable: natural after +/- 6 hours colored: 12 hours Lightly walkable after 24 hours. Fully cured after +/- 10 days
Sanding grit:	P 100-120
Storage/transport:	between 5°C and 25°C
Disposal:	Dispose of residue and empty packaging in accordance with local ordinances.

DATOS TÉCNICOS

Tipo de producto:	base de disolvente
Viscosidad:	+/- 50 s - DIN 4 mm
Materias sólidas:	+/- 47 %
Grado de brillo:	Ultramate
Proporción de mezcla:	Endurecedor UA opcional: 100/5
Potlife:	+/- 3 horas tras añadir el endurecedor
Limieza:	Cleaning Thinner Ciranova®
Número de colores:	16 colores
Rendimiento:	450-550 sq.ft./L por capa 1700 - 2080 sq.ft./gal por capa
Tiempo de secado:	Capa reaplicable: natural tras +/- 6 horas con color: 12 horas Pueden colocarse cargas ligeras encima tras 24 horas. Secado completo tras +/- 10 días
Grano de lijado:	P 100-120
Almacenamiento/transporte:	entre 5 °C y 25 °C
Desecho:	Deseche los residuos y envases vacíos de acuerdo con sus ordenanzas locales.



1QT

5L



PREPARATION

Make sure that all old finish coats are completely removed and that the wood is free from dust and other dirt. Can be used on sanded, planed, and brushed wood. Pre-wetting the wood can give a more intensive stain.

APPLICATION

Stir and shake well before and during use. Apply HARDWAXOIL MAGIC evenly with a buffing machine or a brush. Let the Hardwaxoil Magic settle and remove any excess oil within a few minutes by brushing it with a pad or cloth until the surface feels hand-dry. Hardwood like oak require 2 layers. Multiple layers can be applied for softwood. For exotic wood types, the Hardwaxoil Magic should be tested beforehand. **OPTIONAL: A HARDENER UA (5%) CAN BE ADDED TO INCREASE THE CHEMICAL AND MECHANICAL RESISTANCES.** For industrial applications (rolling, spraying) the Ciranova® technical service should be consulted.

FINISHING

A colored oil should subsequently be finished with a layer of Hardwaxoil TITAN (roller application).

MAINTENANCE

For regular maintenance, we recommend Ciranova® Flooring Soap. For periodic maintenance, use Ciranova® Maintenance Oil or first use Ciranova® Intensive Cleaner in case of heavy dirt. Hardwaxoil MAGIC is only fully hardened after +/- 7 days. During this period, the wood cannot be treated with water or maintenance products.

IMPORTANT INFORMATION ⚠

Dried oil residue is self-igniting. Used pads and clothes must be submerged in water after use. The final color depends on the wood type, sanding, and the amount applied. **That is why it is recommended to always test the color beforehand!**