

COLORS COLORES

PINK BLOCKER 2C

Water-based reactive stain which neutralizes the pink appearance of wood. Also suitable for wood types which do not contain tannin.

- » Neutralizes the pink appearance of certain wood species.
- » Above all for use on red oak.
- » Can be finished afterwards with any product from the Ciranova® line.

PINK BLOCKER 2C

Tinte reactivo con base de agua que neutraliza el aspecto de color rosa de la madera. También para las clases de madera que no contienen taninos.

- » Neutraliza el aspecto de color rosa.
- » A usar principalmente en roble rojo.
- » Puede combinarse con todos los productos de la gama Ciranova®.

TECHNICAL DATA

Product type:	waterborne
Mixing ratio:	50/50
Potlife:	12 hours
Cleaning:	water
Coverage:	160-220 sq.ft./L / 610 - 830 sq.ft./gal
Drying times:	+/- 12 hours
Sanding grit:	P 100-120
Storage/transport:	between 5°C and 25°C
Disposal:	Dispose of residue and empty packaging in accordance with local ordinances.

DATOS TÉCNICOS

Tipo de producto:	base de agua
Proporción de mezcla:	50/50
Potlife:	12 hours
Limieza:	agua
Rendimiento:	160-220 sq.ft./L / 610 - 830 sq.ft./gal
Tiempo de secado:	+/-12 horas
Grano de lijado:	P 100-120
Almacenamiento/transporte:	entre 5 °C y 25 °C
Desecho:	Deseche los residuos y envases vacíos de acuerdo con sus ordenanzas locales.



PREPARATION

Make sure that all old finish coats are completely removed and that the floor is free from dust and other dirt. Can be used on sanded, planned and brushed wood. Pre-wetting the wood can reduce the risk of overlapping.

APPLICATION

Mix the PINK BLOCKER CLEAR with the PINK BLOCKER STAIN in a ratio of 1/1. Apply the product evenly with sprayer, roller or brush and then even out with a brush, T-bar or mop.

CAUTION: This is a reactive stain, make sure that the stain is evenly applied. Respect the reaction time because surrounding temperature, atmospheric humidity and ventilation can influence the reaction time.

FINISHING

Pink Blocker can "pop" the grain so it is suggested that you smoothen the surface after the full reaction time with a buffing pad. Afterwards, the surface should be made dust free, prior to finishing with an oil or waterborne finish from the Ciranova® range. Please contact Ciranova® Technical Support for information about using a waterborne finish.

IMPORTANT INFORMATION ⚠

Only use corrosion-resistant materials. Clean all materials with water immediately after use. The final color depends on the wood type, sanding, preparation and the quantity applied. **It is therefore recommended to always test the color in advance!**