

COLORS COLORES

REACTIVE STAINS

Reactive stain is a reactive aging stain based on natural and reactive colorants. Reactive stain is especially suitable for aging woods containing tannin. After reaction time, the reactive stain should be finished with oil or waterborne finishes.

- » Reacts with tannin in the wood and creates a unique finish.
- » Endless possibilities in combination with colored oils.
- » Color intensity can easily be adjusted with Reactive stain Clear.

REACTIVE STAIN NT (New Technology)

- » Reacts with tannin in the wood and creates unique smoky and aged finishes
- » Natural looks with corresponding natural protection
- » Can easily be mixed with one another to achieve the desired color

TINTES REACTIVO

Reactive Stain es un tinte reactivo envejecedor basado en colorantes naturales y reactivos. Reactive Stain está especialmente indicado para maderas envejecidas que contienen ácido tánico. Tras el tiempo de reacción, debe aplicarse inmediatamente un acabado al Reactive Stain con aceite o barniz.

- » Reacciona con los taninos de la madera y le da un acabado único.
- » Posibilidades ilimitadas en combinación con aceites con color.
- » La intensidad del color puede ajustarse fácilmente con Reactive Stain Clear.

TINTE REACTIVO NT (nueva tecnología)

- » Reacciona con los taninos de la madera y le da un acabado envejecido y ahumado.
- » Aspecto natural con protección también natural.
- » Puede mezclarse fácilmente para conseguir el color deseado.

TECHNICAL DATA

Product type:	waterborne
Cleaning:	water
Coverage:	100-150 sq.ft./L / 380 - 580 sq.ft./gal
Drying times:	6 hours
Sanding grit:	P 100-120
Storage/transport:	between 5°C and 25°C
Disposal:	Dispose of residue and empty packaging in accordance with local ordinances.

DATOS TÉCNICOS

Tipo de producto:	base de agua
Limieza:	agua
Rendimiento:	100-150 sq.ft./L / 380 - 580 sq.ft./gal
Tiempo de secado:	6 horas
Grano de lijado:	P 100-120
Almacenamiento/transporte:	entre 5 °C y 25 °C
Desecho:	Deseche los residuos y envases vacíos de acuerdo con sus ordenanzas locales.



1L

5L



PREPARATION

Make sure that all old finish coats are completely removed and that the wood is free from dust and other dirt. Can be used on sanded, planed, and brushed wood. Pre-wetting the wood can reduce the risk of overlapping.

APPLICATION

Stir and shake well before and during use. Apply reactive evenly stain in the direction of the wood fiber, even out afterwards. Reactive stain can be applied using a brush or spray gun and subsequently smoothened with a brush or mop.

CAUTION:

This is a reactive stain, make sure that the stain is evenly applied. Respect the reaction time because surrounding temperature, atmospheric humidity and ventilation can influence the reaction time.

FINISHING

Reactive stain can "pop" the grain so it is suggested that you smoothen the surface after the full reaction time with a buffing pad. Afterwards, the surface should be made dust free, prior to finishing with an oil or waterborne finish from the Ciranova® product line. Please contact Ciranova® Technical Support for information about using a waterborne finish.

IMPORTANT INFORMATION ⚠

Only use corrosion-resistant materials. Clean all materials with water immediately afterwards. The final color depends on the wood type, sanding, preparation and the amount applied. **That is why it is recommended to always test the color beforehand!**